cetex® BOND

SUGGESTED DOSAGE (PER 50 KG BAG OF CEMENT)

Application Type	Pure SBR Dosage	Equivalent Water Dilution Ratio	Purpose / Benefit
Standard Repairs & Patching Mortars	**5 to 7.5 kg** (10% to 15% by weight)	**1:1** with water (Yields the 10–15 kg diluted mix)	Improves bond, reduces shrinkage cracks, and boosts flexural strength.
Heavy-Duty Floor Screeds & Overlays	**7.5 to 10 kg** (15% to 20% by weight)	**1:1 or 1.5:1** with water	Provides massive abrasion resistance under heavy traffic.
Waterproof Plastering & Renders	**5 to 6 kg** (10% to 12% by weight)	**1:2 or 1:3** with water	Significantly blocks water ingress and chemical permeation.
Cement Injection Grouting	**3 to 3.5 kg** (~7% by weight)	**1:4 or 1:5** with water	Enhances fluid flow, reduces viscosity, and seals micro-cracks.